



PERFORMANCE DATA

THERMO-SAFE - GP[®] CLEAR AND TINTED LAMINATED PRODUCTS - SINGLE GLAZED

SINGLE GLAZED LAMINATED	Visible Light		Solar Energy						S.T.L (dB)	
	Trans.%	Reflect.%	Total Elim.%	Reflect.%	Absorption.%	Direct Trans.%	S.H.G.C.	Shading Coeff.	U-Value (centre of glass) W/m2.K	S.T.L (dB)
THERMO-SAFE GP [®] CLEAR	88	8	20	7	19	74	0.80	0.92	5.8	33
THERMO-SAFE GP [®] BRONZE	54	6	33	6	38	56	0.67	0.77	5.8	33
THERMO-SAFE GP [®] GREY	42	5	37	6	44	50	0.63	0.73	5.8	33
THERMO-SAFE GP [®] BLUE	76	7	22	7	21	72	0.78	0.90	5.8	33
TRANSLUCENT LAMINATED PRODUCTS										
THERMO-SAFE GP [®] ICE WHITE	63	11	37	11	30	59	0.63	0.72	5.8	33
BODY TINTED LAMINATED PRODUCTS										
THERMO-SAFE GP [®] GREEN	79	8	38	6	44	50	0.62	0.71	5.8	33
THERMO-SAFE GP [®] DEEP GREEN	71	7	48	5	59	36	0.52	0.60	5.8	33

PLEASE NOTE: ALL THE ABOVE PRODUCTS WITH THE EXCEPTION OF BODY TINTED ARE AVAILABLE FROM 6.38mm UP TO 16.38mm .

Above products except Translucent are available in deep colours and in 3 strengths - N.S. - Normal Strength , H.P.R. High penetration Resistance and HI - High Impact.

Above Values have been calculated assuming NFRC 100-2010 design parameter, and are given as an indication only. **U-Values quoted** are "centre of glass" and exclude any frame effects. Slight variations may occur due to manufacturing tolerances. All safety glass supplied by Glass Partners is certified to comply with the requirements of SANS 1263 Part 1.

Thermal safety guarantees are available on application. It is recommended that all heat absorbing laminated safety glass is checked for thermal safety compliance at the design stage of all projects.

Sound transmission Loss (S.T.L.) values are mean, measured at the centre frequency of the 1/3 octave band, over the frequency range 100 to 5000Hz, centre of glass.

Whilst this document was prepared & is presented in good faith, Glass Partners hereby disclaim all liability howsoever arising from any error or omission in it, & for any consequences of relying on it.

WEBSITE : www.glasspartners.co.za

CONTACT : 087 721 1700