



PERFORMANCE DATA

THERMO-SIG GP[®] CLEAR AND TINTED LAMINATED PRODUCTS - DOUBLE GLAZED UNITS

	Visible Light		Solar Energy						S.T.L (dB)	
	Trans.%	Reflect.%	Total Elim.%	Reflect.%	Absorption.%	Direct Trans.%	S.H.G.C.	Shading Coeff.	U-Value (centre of glass) W/m2.K	S.T.L (dB)
DOUBLE GLAZED UNITS OUTER GLASS*										
THERMO-SIG GP [®] CLEAR	78	15	32	11	31	58	0.68	0.79	2.8	37
THERMO-SIG GP [®] BRONZE	48	8	53	9	46	45	0.47	0.54	2.8	37
THERMO-SIG GP [®] GREY	37	7	58	8	52	40	0.42	0.48	2.8	37
THERMO-SIG GP [®] BLUE	68	12	39	11	30	59	0.61	0.70	2.8	37
BODY TINTED LAMINATED PRODUCTS										
THERMO-SIG GP [®] GREEN	70	13	48	8	51	41	0.52	0.60	2.8	37
THERMO-SIG GP [®] DEEP GREEN	65	11	54	7	59	34	0.46	0.53	2.8	37

* DOUBLE GLAZING MAKE UP: 24mm NOMINAL THICKNESS - "THERMO " PRODUCTS - OUTER / 12mm AIR GAP / Float , Toughened or Laminated Clear - INNER

Above products available in deep colours and in 3 strengths - N.S. - Normal Strength , H.P.R. High penetration Resistance and HI - High Impact.

Above Values have been calculated assuming NFRC 100-2010 design parameter, and are given as an indication only. **U-Values quoted** are "centre of glass" and exclude any frame effects. Slight variations may occur due to manufacturing tolerances. All safety glass supplied by Glass Partners is certified to comply with the requirements of SANS 1263 Part 1.

Thermal safety guarantees are available on application. It is recommended that all heat absorbing laminated safety glass is checked for thermal safety compliance at the design stage of all projects.

Sound transmission Loss (S.T.L.) values are mean, measured at the centre frequency of the 1/3 octave band, over the frequency range 100 to 5000Hz, centre of glass.

Whilst this document was prepared & is presented in good faith, Glass Partners hereby disclaim all liability howsoever arising from any error or omission in it, & for any consequences of relying on it.

WEBSITE : www.glasspartners.co.za

CONTACT : 087 721 1700